



101

FIBERED ROOF COATING

PRODUCT DESCRIPTIONS:

DEWITT'S FIBERED ROOF COATING is a medium bodied asphalt coating containing refined asphalt, petroleum solvent, and selected hi-tech non-asbestos fibers. DEWITT'S FIBERED ROOF COATING penetrates and protects sound roofing felts. DEWITT'S FIBERED ROOF COATING remains pliable and expands and contracts with the changes of temperature. Apply directly from the can to a variety of roof and outside wall surfaces, shedding water, insulating and preserving.



USES:

DEWITT'S FIBERED ROOF COATING can be used to resaturate, preserve and protect composition, built-up, smooth and slate surfaced roofs. DEWITT'S FIBERED ROOF COATING can also be used on metal roofs and siding, exterior foundation walls, and other concrete and masonry surfaces. Also use DEWITT'S FIBERED ROOF COATING as an interplay adhesive between layers of asphalt felt. Do not use on COAL TAR, EPDM, PVC, or TPO roofing systems.

APPLICATION:

Apply DEWITT'S FIBERED ROOF COATING directly from the container. Stir if necessary, before use. Surface should be clean, dry, and free from all dust, dirt and debris. Dried out felts should be primed with DEWITT'S # 104 ASPHALT PRIMER. Repair all crack, breaks, or open seams with DEWITT'S # 201 PLASTIC ROOF CEMENT and reinforcing membrane. If roof is gravel, remove all loose gravel. Apply by brush or spray over entire area.

SPECIFICATIONS:

Meets ASTM 4479 and Federal Specification SS-A694-D, except this material is asbestos free.

PHYSICAL CHARACTERISTICS:

Weight per gal. (approx)	8 lbs.
Flash point (ASTM 093-52)	100° F Min
Drying time	2-3 days, depending on weather conditions
Viscosity at 80° F	100-120 K.U.
Service temperature, extended exposure	-20° to 150° F
Non-Volatile(Fed. Test Meth. 141)	62% Min
Percent of specially processed asphalts	58% Min
Percent of total solids by volume	88% Min
Film thickness of 1gal/100 sq. ft.	8 Mils
Resistance to oils and solvents	Poor
Resistance to sunlight	Good
Resistance to chemicals	Good
Effects of weathering	Slight cracking
Water Resistance	
Under draining conditions	Excellent
Under continuous submersion	Fair
Restrictions	Do not use on tar roofs
Clean up	Mineral Spirits or DEWITT'S REMOVE-IT
Application temperature	25°-100° F (formulated for seasonal use: summer grade, fall/spring grade, winter grade)

COVERAGE:

3 gallons per 100 sq. ft. on built-up roofs and masonry
2 gallons per 100 sq. ft. on metal roofs.

PACKAGING:

55 gal. drum, 5 gal., 1 gal.

CAUTION:

Combustible: Keep away from heat and open flame.
Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.