



110

POLY-PRO COAT

PRODUCT DESCRIPTIONS:

DEWITT'S POLY-PRO COATING is specially formulated, fibered asphaltic coating containing refined asphalts, petroleum solvent, and selected hi-tech non-asbestos fibers. The selected hi-tech fibers promote excellent rheology, yet still allows for excellent spray ability and brush ability. DEWITT'S POLY-PRO COATING penetrates and protects sound roofing felts. DEWITT'S POLY PRO COATING remains pliable and expands and contracts with the change of temperature. Apply directly from container to a variety of roof and outside wall surfaces, shedding water, insulating, and preserving.



USES:

DEWITT'S POLY-PRO COATING can be used to resaturate, preserve and protect composition, built-up, smooth and slate surfaced roofs. DEWITT'S POLY PRO COATING can be also used on metal roofs, siding, exterior foundation walls, and other concrete and masonry surfaces. Also use as an interplay adhesive between layers of asphalt felts. Use with polyester as a base and top coat.

APPLICATION:

Stir if necessary, before use. Surface should be clean, dry and free from all dust or materials. Dried out felts should be primed with DEWITT'S PRO ASPHALT PRIMER (#154). Repair all cracks, breaks, or open seams with DEWITT'S PRO FLASH CEMENT (#251) and reinforcing membrane.

SPECIFICATIONS:

Meets ASTM Specifications D-4479 and Federal Specification SS-A-694D, ASTM D-2823, except this material is asbestos free.

PHYSICAL CHARACTERISTICS:

| | |
|--|---|
| Weight per gallon (approx) | 8lbs |
| Flash point | 100°F Min |
| Drying time | 2-3 days, depending on weather conditions |
| Viscosity at 80 °F | 100 – 120 K.U. |
| Service temperature, extended exposure | -20° - 150°F |
| Non-Volatile (Fed. Test Method 141) | 62% Min |
| Percent of specially processed asphalt | 58% Min |
| Percent of total solids by volume | 88% Min |
| Film thickness of 1gal / 100 sq. ft. | 8 Mills |
| Resistance to oils and solvents | Poor |
| Resistance to sunlight and chemicals | Good |
| Effects of weathering (ASTM 2823) | Slight Cracking |
| Water Resistance | |
| Under good drainage conditions | Excellent |
| Under continuous submersion | Fair |
| Clean up | Mineral Spirits or DEWITT'S REMOVE-It |
| Application temperature | 25° - 100°F (Formulated for seasonal use summer grade, spring/fall grade, winter grade) |

COVERAGE:

3 gallons per 100 sq. ft. on built up roofs and masonry.
2 gallons per 100 sq. ft. on metal roofs

PACKAGING:

55 gallon drum, & 5 gallon pail.

CAUTION:

Combustible: Keep away from heat and open flame.
Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.