



151

PRO COAT FIBER ROOF COATING

PRODUCT DESCRIPTIONS:

DEWITT'S FIBER ROOF COATING is a medium bodied asphalt coating containing refined asphalts, petroleum solvent, and selected hi-tech non-asbestos fibres. DEWITT'S PRO COAT FIBER ROOF COATING penetrates and protects sound roofing felts. DEWITT'S FIBER ROOF COATING remains pliable and expands and contracts with the change of temperature. Apply directly from the can to a variety of roof and outside wall surfaces, shedding water, insulating and preserving.



USES:

DEWITT'S FIBER ROOF COATING can be used to resaturate, preserve and protect composition, built-up, smooth and slate surfaced roofs. DEWITT'S PRO COAT FIBER ROOF COATING can also be used on metal roofs, siding, exterior foundation walls, and other concrete and masonry surfaces. Also use as an interply adhesive between layers of asphalt felts. Do not use coating on EPDM, TPC, or PVC roofs. DEWITT'S PRO COAT FIBER ROOF COATING can be used on SBS MODIFIED roofs.

APPLICATION:

Stir DEWITT'S PRO COAT FIBRE ROOF COATING before use. Surface should be clean, dry and free from all dust or materials. Dried out felts should be primed with DEWITT'S PRO ASPHALT PRIMER (#154). Repair all cracks, breaks, or open seams with DEWITT'S ROOFING CEMENTS (#251, #252, or # 253), and reinforcing membrane.

SPECIFICATIONS:

Meets ASTM Specifications D-4479 and Federal Specifications SS-A-694D, except this material is asbestos free.

PHYSICAL CHARACTERISTICS:

Weight per gallon (approx.)	8 lbs.
Flash Point	100°F Min
Drying time	2-3 days, depending on weather conditions
Viscosity at 80 °F	100-120 K.U.
Service temperature, extended exposure	-20°- 150°F
Non-Volatile (Fed. Test Method 141)	62% Min
Percent of specially processed asphalt	58% Min
Percent of total solids by volume	88% Min
Film thickness of 1gal/100 sq. ft.	8 Mills
Resistance to oils and solvents	Poor
Resistance to sunlight and chemicals	Good
Effects of weathering	Slight cracking
Water Resistance	
Under good drainage conditions	Excellent
Under continuous submersion	Fair
Clean up	Mineral Spirits or DEWITT'S REMOVE-It
Application temperature	25°-100°F(formulated for seasonal use: summer grade, fall/spring grade, winter grade)

COVERAGE:

3 gallons per 100 sq. ft. on built-up roofs and masonry.
2 gallons per 100 sq. ft. on metal roofs

PACKAGING:

55 gallon drum, & 5 gallon pail.

CAUTION:

Combustible: Keep away from heat and open flame.
Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.