



SILVER SHIELD 300

ALUMINUM ROOF COATING

PRODUCT DESCRIPTION:

DEWITT'S SILVER SHIELD 300 ALUMINUM ROOF COATING is a solvent type, asphalt based coating that is similar to conventional roof coatings. Manufactured with special blend asphalts, refined oils, mineral stabilizers and reinforced with hi-tech asbestos-free fibers. Aluminum coatings provide a tough continuous coating with extra-long life and good initial brightness. Aluminum pigment gives it a bright, metallic aluminum color when applied on metal, tile, conventional bituminous roof surfaces and modified bitumen. This reflective coating reduces the deteriorating effect of the sun's rays, reduces interior temperature, and protects roof surfaces from excessive weathering.



USES:

DEWITT'S SILVER SHIELD 300 can be used on old asphalt roofs, smooth or mineral surfaced, silos, metal roofs and siding, water towers, modified bitumen, mobile homes, campers, and RV's. Aluminum coatings can reduce interior temperatures up to 15°F and serve as a rust inhibitor and anti-corrosive agent.

APPLICATION:

Surfaces must be dry, and free of dirt, dust, and debris. Dried out roofs should be primed with DEWITT'S ASPHALT PRIMER (#154). Repair all cracks, breaks, or open seams with DEWITT'S PRO FLASH ROOF CEMENT (#251). Do not apply when rain appears imminent or less than four hours before surface can be expected to be covered with dew. DEWITT'S SILVER SHIELD 300 is ready to use from the container. Moderate stirring is required to mix pigment. Stir after each application. Apply with roof brush, squeegee, or spray gun. When brushing, brush last strokes all in one direction.

RESTRICTIONS:

Do not use on dead level asphalt, tar base, or gravel roofs. Concrete surfaces must be primed with DEWITT'S ASPHALT PRIMER (#154). Freshly coated hot bituminous roofs should be allowed to weather at least 3 months. Roofs patched or primed should weather at least 10 days. Modified bitumen roofs should weather 30-90 days before application.

SPECIFICATIONS:

Meets Federal Specification TT-C-498C, ASTM D-2824-85, Type III, except this material is asbestos free. Pigment Specification ASTM D-962. Contains 3 lbs. of aluminum paste per gallon.

PHYSICAL CHARACTERISTICS:

Weight per gal. (approx) 8 lbs.
Flash point (ASTM 093-52) 100° F Min
Drying time 8 Hrs Min
Viscosity at 80° F 35 Sec

Service temperature, extended -20° to 180° F

exposure

Resistance to oils and solvents Poor Resistance to sunlight and chemicals Excellent

Water Resistance

Under draining conditions Excellent Under continuous submersion Poor

Clean up Mineral Spirits or Naphtha

Application temperature 25°-100°F(formulated for seasonal use:

summer grade, spring/fall

grade, winter grade)

COVERAGE:

2 gallons per 100 sq. ft. on roofing felts and masonry. 1.5 gallons per 100 sq. ft. on metal.

PACKAGING:

55 gallon drum & 5 gallon

CAUTION:

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.