



766

RUBBER SEAL BUTYL SPLICE ADHESIVE

PRODUCT DESCRIPTION:

RUBBER SEAL BUTYL SPLICE ADHESIVE is a Butyl-based contact adhesive with high initial green strength and excellent durability.

USES:

RUBBER SEAL BUTYL SPLICE ADHESIVE can be used to adhere two cleaned surfaces of EPDM single-ply membrane to each other.

APPLICATION:

RUBBER SEAL BUTYL SPLICE ADHESIVE should be applied at temperatures of 40°F or above. Applying the BUTYL SPLICE ADHESIVE at temperatures below 40°F will extend drying times and potentially cause condensation of water on the membrane surface producing lower ultimate bond strengths. If RUBBER SEAL BUTYL SPLICE ADHESIVE is stored below 40°F, store the BUTYL SPLICE ADHESIVE at room temperature (72°F) for at least three days before using.

Apply RUBBER SEAL BUTYL SPLICE ADHESIVE with a brush. Brush a coat of adhesive on both EPDM surfaces to be bonded. Air dry 15 - 45 minutes at ambient temperatures until adhesive is tacky to the touch, but will NOT transfer to a gloved finger. Bond with sufficient pressure to assure intimate contact of the coated surfaces.

PACKAGING:

1 gallon, 5 gallon

COVERAGE:

150-200 Linear feet, 3" wide splice

HANDLING:

RUBBER SEAL BUTYL SPLICE ADHESIVE contains ingredients which could be harmful if mishandled. Contact with skin and eyes should be avoided and necessary protective equipment and clothing should be worn. All 5 gallon pails should be

grounded and/or bonded when material is transferred. Vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors, static discharge, or other ignition sources at location distant from material handling point.

STORAGE:

When RUBBER SEAL BUTYL SPLICE ADHESIVE is stored indoors, out of direct sunlight, and in the original, unopened container between 60°F and 80°F, the shelf life is nine months. Always rotate stock.

