



152

PRO WET-STICK FIBERED ROOF COATING

PRODUCT DESCRIPTION:

DEWITT'S PRO WET-STICK FIBER ROOF COATING is an all purpose roof coating manufactured with special blend asphalt, refined oils, mineral stabilizers and reinforced with hi-tech asbestos-free fibers. DEWITT'S PRO WET-STICK FIBER ROOF COATING sets up to form a tough, continuous, moisture-proof film that will retain its pliability for a long period of time. This enables it to expand and to conform to movement of other materials. DEWITT'S PRO WET-STICK FIBER ROOF COATING penetrates and protects sound roofing felts.



Remains pliable, expands and contracts with the change of temperature. Apply directly from can to a variety of roof and outside wall surfaces, shedding water, insulating and preserving. DEWITT'S PRO WET-STICK FIBER ROOF COATING can be used on wet or dry surfaces.

USES:

DEWITT'S PRO WET-STICK FIBER ROOF COATING can be used to resaturate, preserve, and protect composition, built-up, smooth, and slate surfaced roofs. DEWITT'S PRO WET-STICK FIBER ROOF COATING can also be used on metal roofs, siding, exterior foundation walls, and other concrete and masonry surfaces. Also use as an inter-ply adhesive between layers of asphalt felts. Do not use on COAL TAR, EPDM, TPD, or PVC type roofs. This product can be used on SBS Modified roofs.

APPLICATION:

Stir if necessary before use. Surface should be clean, free of all dirt, dust, debris, and materials. Dried out felts should be primed with DEWITT'S #154 ASPHALT PRIMER. Repair all cracks, breaks, or open seams with DEWITT'S #252 WET-STICK ROOF CEMENT, DEWITT'S #253 PRO FLASH XTRA, or DEWITT'S #251 PRO FLASH.

SPECIFICATIONS:

Meets ASTM Specifications D-4479-85 and Federal Specifications SS-A-694D, except this material is asbestos free.

PHYSICAL CHARACTERISTICS:

Weight per gallon (approx.)	8 lbs.
Flash Point	100°F Min
Drying time	2-3 days, depending on weather conditions
Viscosity at 80°F	100-120 K.U.
Service temperature, extended exposure	-20°- 150°F
Non-Volatile (Fed. Test Method 141)	62% Min
Percent of specially processed asphalt	58% Min
Percent of total solids by volume	88% Min
Film thickness of 1gal/100 sq. ft.	8 Mils
Resistance to oils and solvents	Poor
Resistance to sunlight and chemicals	Good
Specific Gravity at 77°F	.427
Water Resistance	
Under good drainage conditions	Excellent
Under continuous submersion	Fair
Clean up	Mineral Spirits or DEWITT'S REMOVE-It
Application temperature	25°-100°F (formulated for seasonal use: summer grade, fall/spring grade, winter grade)

COVERAGE:

1 ½ -2 gallons per 100 sq. ft. on built-up roofs and masonry.
1 gallons per 100 sq. ft. on metal roofs

PACKAGING:

55 gallon drum, 5 gallon & 1 gallon.

CAUTION:

Combustible: Keep away from heat and open flame.
Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.