



155

# PRO RESATURANT

---

## PRODUCT DESCRIPTION:

DEWITT'S PRO RESATURANT is a special blend of selected asphalt, hi-tech fibers, and a mixture of various kinds of penetrating oils. These oils soak down into the existing roof mat to help rejuvenate the old asphalt to the original condition. A thick layer of asphalt remains on the surface to protect it from ultra-violet rays of the sun as well as serve as a binder for the replacement of the gravel or slag.



## USES:

Use on BUR roofs, especially old and dried out roofs. DO NOT use on COAL TAR, EPDM, TPO or PVC roofing systems.

## APPLICATION:

Remove all loose gravel, dirt, dust, and debris from the surface by sweeping or power broom. If gravel is to be used, it must be free of silt. Repair all blisters, breaks, or holes in the roof with DEWITT'S #251 PRO FLASH FLASHING CEMENT or DEWITT'S #252 PRO "WET-STICK" FLASHING CEMENT and reinforcing membrane.

BRUSH - Pour directly from the container and spread with a thick fiber roof brush at the rate of 5-8 gallons per 100 sq. ft.

SPRAY - Apply on large areas with standard mastic pump type equipment that is placed in the material drum. The coating should be sprayed on in one coat at the rate of 5-8 gallons per 100 sq. ft. applied with 50% overlap of the spray pattern so as to obtain a uniform and continuous film.

After application, gravel should be re-applied at the rate of 400 lbs per 100sq ft.

## SPECIFICATIONS:

Meets ASTM Specifications D-4479 and Federal Specifications SS-A-694D, except this material is asbestos free.

## PHYSICAL CHARACTERISTICS:

Weight per gallon (approx.)	8 lbs
Flash Point	100°F Min
Drying Time	2-3 days, depending on weather conditions
Viscosity at 80°F	100-120 K.U
Service temperature, extended exposure	-20°F - 150°F
Non-Volatile (Fed Test Method 141)	62% Min
% Specially processed asphalt	58% Min
% of Total Solids by Volume	88% Min
Film thickness of 1 gal/100 sq ft	8 Mils
Resistance to oils and solvents	Poor
Resistance to sunlight and chemicals	Good
Effects of weathering	Slight cracking
Water Resistance	
Under good drainage conditions	Excellent
Under continuous submersion	Fair
Clean up	Mineral spirits or DeWitt's Remove-It
Application temperature	25°F - 100°F (formulated for seasonal use; summer grade, fall/spring grade, winter grade)

## COVERAGE:

3 gallons per 100 sq ft on BUR

## PACKAGING:

55 gallon drum & 5 gallon pail

## CAUTION:

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.