

PRODUCT CODE: 152

PRO WET-STICK FIBERED ROOF COATING

DESCRIPTION

DEWITT'S PRO WET-STICK FIBER ROOF COATING is an all purpose roof coating manufactured with special blend asphalt, refined oils, mineral stabilizers and reinforced with hi-tech asbestos-free fibers. DEWITT'S PRO WET-STICK FIBER ROOF COATING sets up to form a tough, continuous, moisture-proof film that will retain its pliability for a long period of time. This enables it to expand and to conform to movement of other materials. DEWITT'S PRO WET-STICK FIBER ROOF COATING penetrates and protects sound roofing felts. Remains pliable, expands and contracts with the change of temperature. Apply directly from can to a variety of roof and outside wall surfaces, shedding water, insulating and preserving. DEWITT'S PRO WET-STICK FIBER ROOF COATING can be used on wet or dry surfaces.

USES

DEWITT'S PRO WET-STICK FIBER ROOF COATING can be used to resaturate, preserve, and protect composition, built-up, smooth, and slate surfaced roofs. DEWITT'S PRO WET-STICK FIBER ROOF COATING can also be used on metal roofs, siding, exterior foundation walls, and other concrete and masonry surfaces. Also use as an inter-ply adhesive between layers of asphalt felts. Do not use on COAL TAR, EPDM, TPD, or PVC type roofs. This product can be used on SBS Modified roofs.

APPLICATION

Stir if necessary before use. Surface should be clean, free of all dirt, dust, debris, and materials. Dried out felts should be primed with DEWITT'S #154 ASPHALT PRIMER. Repair all cracks, breaks, or open seams with DEWITT'S #252 WET-STICK ROOF CEMENT, DEWITT'S #253 PRO FLASH XTRA, or DEWITT'S #251 PRO FLASH.

SPECIFICATIONS

Meets ASTM Specifications D-4479-85 and Federal Specifications SS-A-694D, except this material is asbestos free.

COVERAGE

1 $\frac{1}{2}$ -2 gallons per 100 sq. ft. on built-up roofs and masonry. 1 gallons per 100 sq. ft. on metal roofs

PACKAGING

55 gallon drum, 5 gallon & 1 gallon.

CAUTION

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.



PHYSICAL CHARACTERISTICS

THIOTOAL OHARAOTER	101100
WEIGHT PER GAL (APPROX.)	8 lbs
FLASH POINT (ASTM 093-52)	100° F Min
DRYING TIME	2-3 days, depending on weather conditions
VISCOSITY AT 80° F	100 - 120 K.U.
SERVICE TEMPERATURE (EXTENDED EXPOSURE)	-20° to 150° F
NON-VOLITILE (FED. TEST METHOD 141)	62% Min
PERCENT OF SPECIALLY PROCESSED ASPHALT	58% Min
PERCENT OF TOTAL SOLIDS BY VOLUME	88% Min
FILM THICKNESS OF 1GAL/100 SQ. FT.	8 Mils
RESISTANCE TO OILS AND SOLVENTS	Poor
RESISTANCE TO SUNLIGHT AND CHEMIC	ALS Excellent
SPECIFIC GRAVITY AT 77°F	.427
WATER RESISTANCE UNDER DRAINING CONDITIONS UNDER CONTINUOUS SUBMERSION	Excellent Fair
CLEAN UP	Mineral Spirits or DEWITT'S REMOVE-
APPLICATION TEMPERATURE	25°-100° F (formulated for seasonal use: summer grade, fall/ spring grade, winter grade)