



PRODUCT CODE: 253

PRO FLASH XTRA

DESCRIPTION

DEWITT'S PRO FLASH XTRA FLASHING CEMENT is a rubberized, heavy-trowel consistency asphalt, refined oils, mineral stabilizes, and is reinforced with hi-tech, asbestos-free fibers to make a heavy-duty trowel-grade flashing cement. PRO FLASH XTRA FLASHING CEMENT can be used on wet or dry surfaces.

PRO FLASH XTRA FLASHING CEMENT will not sag or slump, thus permitting heavy application on vertical surfaces. PRO FLASH XTRA FLASHING CEMENT is a tough, flexible, waterproof, corrosive-proof cement that is extra smooth and fast to apply. PRO FLASH XTRA FLASHING CEMENT is rubberized to perform over a wide range of temperature conditions, eliminating chipping or cracking in cold weather and sliding or bleeding in warm weather. PRO FLASH XTRA FLASHING CEMENT summer grade application range is approximately 30°-120° F. Winter grade application range is approximately 0°-80° F.

USES

DEWITT'S PRO FLASH XTRA FLASHING CEMENT is an excellent cement for repair of flashing and is ideal for vertical surface application around roofs, parapet walls, chimneys, valleys, pipes, and foundations. This flashing cement can also be used for repairing leaks in shingles, concrete, metal, or asphalt roofs, downspouts, cornices, skylights, etc. PRO FLASH XTRA FLASHING CEMENT is an excellent sealant for expansion joints and cracks in concrete and brick, and as a joint filler for precast roof slabs. PRO FLASH XTRA FLASHING CEMENT is compatible with SBS Roof Systems.

APPLICATION

DEWITT'S PRO FLASH XTRA FLASHING CEMENT is used directly from the container. Apply with a trowel or putty knife to surfaces that must be free of dirt, dust and debris. For flashings, apply 1/8" to 1/2" thick and trowel it down to a smooth feather edge. On thick applications, reinforce area with membrane. For patching, apply PRO FLASH XTRA FLASHING CEMENT over area 3/8" to 1/2" thick. Application on a wet surface requires cement to be worked into surface for best results.

SPECIFICATIONS

Meets ASTM 4586-86 and Federal Specification SS-C-153C ASTM D-2822 Type I, except this material is asbestos free.

COVERAGE

One gallon covers approximately 15 - 20 sq. ft. at 1/8" thick

PACKAGING

55 gallon drum, 5 gallon, 3 gallon, 10.3oz cartridges

CAUTION

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.



PHYSICAL CHARACTERISTICS

WEIGHT PER GAL (APPROX.)	9 lbs
FLASH POINT (ASTM 093-52)	100° F Min
DRYING TIME	2-3 days, depending on weather conditions
VISCOSITY AT 80° F	Medium to heavy trowel
SERVICE TEMPERATURE (EXTENDED EXPOSURE)	-40° to 180° F
RUBBERIZED	SBS
RESISTANCE TO OILS AND SOLVENTS	Poor
RESISTANCE TO SUNLIGHT	Excellent
RESISTANCE TO CHEMICALS	Excellent
EFFECTS OF WEATHERING	Minimal
WATER RESISTANCE	
UNDER DRAINING CONDITIONS	Excellent
UNDER CONTINUOUS SUBMERSION	Fair
RESTRICTIONS	Do not use on coal tar roofs
CLEAN UP	Mineral Spirits or DEWITT'S REMOVE-IT
APPLICATION TEMPERATURE	Summer grade: 30° - 120° F Winter grade: 0° - 80° F