# NEO-SEAL NEOPRENE ROOF CEMENT

#### DESCRIPTION

DEWITT'S NEO-SEAL NEOPRENE ROOF CEMENT is an elastomeric, trowel-consistency cement manufac-tured with neoprene rubber and hi-tech mineral fibers to produce a rubberized gun grade or trowel grade flashing or patching cement.

#### USES

DEWITT'S NEO-SEAL NEOPRENE ROOF CEMENT is an excellent elastomeric cement for construction and repairs of flashing. It is an ideal sealant for expansion joints and cracks, and repairing leaks in many roofing applications such as parapet walls, chimneys, valleys, vent pipes, SBS modified, gutters, downspouts, skylights, etc. Do not use as shingle tab cement.

#### **APPLICATION**

DEWITT'S NEO-SEAL NEOPRENE ROOF CEMENT is easy to apply using a trowel or caulking gun. Surfaces must be dry, free of dirt, dust, oil, and debris. Replace or repair all drawn-up nails with larger nails before patching. Cut open any breaks or blisters and allow to dry.

#### COVERAGE

One gallon covers approximately 7-10 sq. ft. at 1/4" thick.

#### PACKAGING

5 gallon, 3 gallon, 1 gallon, 10.3oz cartridges

### **CAUTION**

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed. Avoid prolonged or repeated contact with skin and breathing vapors. Use only with adequate ventilation. DO NOT USE for shingle tab cement. May not be compatible with some one-ply roofing systems. Check with manufacturer before use.



## **PHYSICAL CHARACTERISTICS**

WEIGHT PER GAL (APPROX.)	9.65 lbs
FLASH POINT (ASTM 093-52)	105° F Min
DRYING TIME TOUCH CURE	4 hours 10 - 14 days
RESISTANCE TO OILS AND SOLVENTS	Good
RESISTANCE TO SUNLIGHT	Excellent
RESISTANCE TO WATER	Good
CLEAN UP	Mineral Spirits or DEWITT'S REMOVE-
	IT
APPLICATION TEMPERATURE	40°F



DeWitt Products Company | 5860 Plumer St, Detroit, MI 48209 Phone: (313) 554 - 0575 | Fax: (313) 554 - 2171 www.dewittproducts.com

Juality Since