



PRODUCT CODE: 318

COOL-TOP WHITE THERMOPLASTIC SEBS COATING

DESCRIPTION

DEWITT'S COOL-TOP WHITE THERMOPLASTIC SEBS COATING is specially formulated with excellent elongation and tensile strength to resist cracking and withstand harsh conditions. Its high flexibility, and brilliant white color give roofs longer life, saves energy and provides cooler interior temperatures.

USES

DEWITT'S COOL-TOP WHITE THERMOPLASTIC SEBS COATING can be used on metal, EPDM, TPO, BUR roofs, cement, aged aluminum roof coating, hypalon, modifieds, and masonry.

APPLICATION

Apply when temperatures are above 40°F. Do not apply if heavy dew or rain is expected within 24-48 hours. Make sure roof is dry before application. Drying time: approximately 6 hours at 73°F/50% humidity. Two coats recommended allowing first coat to dry 24 hours.

1. Surfaces must be clean and free of dust, dirt, oil, moisture, loose granules, gravel, peeling paint or other foreign matter. Rusty metal must be wire brushed of loose rust and primed with a metal rust primer. Power washing is recommended.
2. PATCHING & SEAMS use DEWITT'S WET-STICK THERMOPLASTIC.
3. Stir COOL-TOP WHITE THERMOPLASTIC SEBS COATING before application. Spray (airless sprayer), brush, or roll (3/8 nap" exterior roller) to surface (Step 3). Do not thin.

COVERAGE

80-100 sq. ft. per gallon/coat

PACKAGING

5 gallon bucket

CAUTION

Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Keep out of reach of children. Read SDS prior to use. For professional use only.



PHYSICAL CHARACTERISTICS

| | |
|---------------------------|---------------------------------------|
| WEIGHT PER GAL (APPROX.) | 7.3 lbs |
| FLASH POINT | 104° F |
| DRYING TIME | 24 hours (at 73° F) |
| NON-VOLATILE (ASTM D2369) | 51.69% |
| PERMEANCE | .57 US perm @ 23 Mil |
| TENSILE PROPERTIES | |
| TENSILE STRENGTH | 2,172 PSI |
| ELONGATION | 439% |
| CLEAN UP | Mineral Spirits or DEWITT'S REMOVE-IT |
| APPLICATION TEMPERATURE | Temperatures above 40° F |